

# MACHINING CONDITIONS - TURNING - DEPTH OF CUT AND FEED

## RCMT 0803 M0

Material Group	Lamina Gr. N°	Material Examples	Hardness	DOC [mm]		Feed [mm/rev]		Amax [mm <sup>2</sup> ]	Suggested Starting Parameters		
				min	max	min	max		DOC	Feed	
P	Non Alloyed	C35, Ck45, 1020, 1045, 1060, 28Mn6	125 HB	0.50	2.40	0.15	0.40	0.77	1.20	0.35	
			190 HB							0.30	
			250 HB							0.30	
	Low Alloyed	2	42CrMo4, S150, Ck60, 4140, 4340, 100Cr6	180 HB	0.50	2.40	0.15	0.35	0.67	1.20	0.30
				230 HB							
				280 HB							
				350 HB							
	High Alloyed	3	X40CrMoV5, H13, M42, D3, S6-5-2, 12Ni19	220 HB	0.50	2.40	0.13	0.30	0.35	1.20	0.30
				280 HB							0.28
				320 HB							0.24
				350 HB							0.24
	M	Austenitic	4	304, 316, X5CrNi18-9	0.50	2.40	0.14	0.35	0.38	1.20	0.30
240 HB											0.29
Duplex		5	X2CrNiN23-4, S31500	290 HB	0.50	1.80	0.13	0.30	0.36	1.20	0.28
				310 HB							
Ferritic & Martensitic		6	410, X6Cr17, 17-4PH, 430	200 HB	0.50	2.40	0.15	0.35	0.38	1.20	0.25
				42 HRc							0.22
K	Grey	7	GG20, GG40, EN-GJL-250, N030B	0.50	2.40	0.11	0.45	0.84	1.20	0.35	
											200 HB
											250 HB
	Malleable & Nodular	8	GGG40, GGG70, 50005	150 HB	0.50	2.40	0.11	0.35	0.72	1.20	0.30
				200 HB							
				250 HB							
S	Fe, Ni & Co based	9	Incoloy 800	0.50	1.80	0.13	0.30	0.36	1.20	0.28	
			Inconel 700								
			Stellite 21								
	Ti based	10	T40	0.50	1.80	0.13	0.32	0.38	1.20	0.30	
			TiAl6V4							0.28	
			-								
H	Steel	11	X100 CrMo13, 440C, G-X260NiCr42	0.50	1.40	0.05	0.22	0.24	1.10	0.18	
										50 HRc	0.16
										55 HRc	0.12
										400 HB	0.18
										55 HRc	0.12
Chilled Cast Iron	White Cast Iron	12	AlSi12	0.50	2.40	0.15	0.40	0.84	1.20	0.35	
											130 HB

The depth of cut and feed rate tables are for the geometry and corner radius specified above the table. Refer to cutting speed tables on pages 186 and 187 for recommended materials per grade.